

BEST AVAILABLE COPY

TITLE COAT WEIGHT OF FORMULATIONS #1-6 Book No. 24
FROM PP143-149

153

From Page No. _____

#	Formulation	Coat weight plus 1 mil PET	* 0.03155 P69 - 1 mil PET	COAT WEIGHT / 10 CM ²
P143	1430 / 1/2 PD / 15 Sel FB	0.13925	0.1077	$\bar{x} = 113.6 \text{ MG} \pm 6.27 (5.5\%)$
	" " "	0.1517	0.1202	
	" " "	0.1445	0.1130	
P143	1430 / 1/2 PD / 15 Sel FB	0.1647	0.1332	$\bar{x} = 133.17 \text{ MG} \pm 0.75 (0.56\%)$
	" " "	0.1639	0.1324	
	" " "	0.1654	0.1339	
P144	1753 / 15 Sel FB	0.1612	0.1297	$\bar{x} = 129.97 \text{ MG} \pm 0.38 (0.29\%)$
	" " "	0.1613	0.1298	
	" " "	0.1619	0.1304	
P144	1753 / 1/2 PD / 15 Sel FB	0.1863	0.1548	$\bar{x} = 156.13 \text{ MG} \pm 1.89 (1.2\%)$
	" " "	0.1898	0.1583	
	" " "	0.1868	0.1553	
P147	1430 / 1/2 PD / 11.3 Sel FB	0.1833	0.1518	$\bar{x} = 148.97 \text{ MG} \pm 4.23 (2.8\%)$
	" " "	0.1825	0.1510	
	" " "	0.1756	0.1441	
P147	1753 / 1/2 PD / 11.3 Sel FB	0.1458	0.1143	$\bar{x} = 114.4 \text{ MG} \pm 0.36 (0.32\%)$
	" " "	0.1456	0.1141	
	" " "	0.1463	0.1148	

* 1.0 mil PET 0.03155 on P69 this notebook

To Page No. _____

Witnessed & Understood by me,

[Signature]

Date

Invented by

Date

Recorded by

[Signature]